Appl. No. : 09/776,383 Filed : 02/02/2001

## AMENDMENTS TO THE CLAIMS

1-3. (Cancelled)

/ M. (Previously presented) A process for preparing an organic silicate polymer having a flexible bridge unit in the network comprising the step of:

reacting the following component (a) with the following component (b) in an organic solvent after addition of water and catalyst:

- (a) organosilane of the formula  $R^1_m R^2_n SiX_{4-m-n}$  (where each of  $R^1$  and  $R^2$  which may be the same or different, is a non-hydrolysable group selected from hydrogen, alkyl, fluorine-containing alkyl or aryl group; X is a hydrolysable group selected from halide, alkoxy or acyloxy; and m and n are integers of from 0 to 3 satisfying  $0 \le m+n \le 3$ ) or a partially hydrolyzed condensate thereof; and
- (b) organic bridged silane of the formula R<sup>3</sup><sub>p</sub>Y<sub>3-p</sub>Si-M-SiR<sup>4</sup><sub>q</sub>Z<sub>3-q</sub> (where each of R<sup>1</sup> and R<sup>4</sup> which may be the same or different, is a non-hydrolysable group selected from hydrogen, alkyl, fluorine-containing alkyl, alkenyl or aryl; each of Y and Z which may be the same or different, is a hydrolysable group selected from halide, alkoxy or acyloxy; M is alkylene or arylene group; and p and q are integers of from 0 to 2) or a cyclic oligomer with organic bridge unit (Si-M-Si), wherein the organic bridged silane is synthesized by reacting a silane monomer containing a Si-H with a silane monomer containing aliphatic unsaturated carbon (-CH=CH<sub>2</sub>) in the presence of a catalyst.
  - 5-6. (Cancelled)
- 2.7. (Previously presented) The process according to Claim # wherein the organic silicate polymer has a weight average molecular weight of from 500 to 100,000.
  - 8-11. (Cancelled)
- 3 12. (Previously presented) The process according to Claim  $\frac{1}{4}$ , wherein the partially hydrolyzed condensate of the organosilane is obtained by reacting the organosilane of the formula  $R^1_m R^2_n SiX_{4-m-n}$  with water in an organic solvent in the presence of a catalyst.
- 7 13. (Previously presented) The process according to Claim 4, wherein the cyclic oligomer with organic bridge unit (Si-M-Si) is synthesized by the hydrosilylation reaction of an oligomer of ring structure (I):

Appl. No. : 09/776,383 Filed : 02/02/2001

$$L_1 \longrightarrow S_1 \longrightarrow L_2$$

$$L_1 \longrightarrow S_1 \longrightarrow L_2$$

$$L_2 \longrightarrow L_1$$

$$L_2 \longrightarrow L_2$$

$$L_1 \longrightarrow L_2$$

$$L_2 \longrightarrow L_2$$

$$L_1 \longrightarrow L_2$$

$$L_2 \longrightarrow L_2$$

$$L_1 \longrightarrow L_2$$

wherein  $L_1$  is alkenyl; and  $L_2$  is selected from the group consisting of hydrogen, alkyl, and aryl.

(Currently amended) The process according to Claim A, wherein the cyclic oligomer with organic bridge unit (Si-M-Si) is synthesized by the hydrosilylation reaction of an oligomer of ring structure (II):

$$M_1$$
 $M_2$ 
 $M_2$ 
 $M_2$ 
 $M_2$ 
 $M_2$ 
 $M_3$ 
 $M_4$ 
 $M_2$ 
 $M_2$ 
 $M_2$ 
 $M_3$ 
 $M_4$ 
 $M_2$ 
 $M_2$ 

wherein  $M_2$   $M_1$  is alkenyl; and  $M_2$  is selected from the group consisting of hydrogen, alkyl, and aryl.

(Currently amended) The process according to Claim A, wherein the cyclic oligomer with organic bridge unit (Si-M-Si) is synthesized by the hydrosilylation reaction of an oligomer of ring structure (I) and an oligomer of ring structure (II):

wherein  $L_1$  is alkenyl;  $L_2$  is selected from the group consisting of hydrogen, alkyl, and aryl;  $\underline{M}_1$  is alkenyl; and  $M_2$  is selected from the group consisting of hydrogen, alkyl, and aryl.

7 16. (Previously presented) The process according to Claim A, wherein an amount of the organic bridged silane reacted with component (a) is greater than 5 parts by weight per 100 parts by weight of component (a).

Appl. No. : 09/776,383 Filed : 02/02/2001

17-27. (Cancelled)